



pro clima SOLITEX MENTO® ULTRA

Roof Weather Resistive Barrier

SOLITEX MENTO® ULTRA provides superior weather protection for your roof, particularly under high wind conditions. With an extra heavy duty classification (AS/NZS 4200.1), it is suitable to be used in any tile, metal and slate roof applications even with large rafter or truss spacings. SOLITEX MENTO® ULTRA protects your roof and building envelope from the elements during construction, whilst allowing any internal moisture to escape through the vapour permeable, non-porous TEEE⁺ layer.

- ✓ Extra heavy duty classification (AS/NZS 4200.1)
- ✓ Highly vapour permeable (Class 4)
- ✓ Superior strength for high wind areas
- ✓ Weathertight & airtight weather resistive barrier (WRB)
- ✓ Helps protect buildings from condensation

Declare.



19 07 2021



Your local support

1800 PRO CLIMA (776 254)

Technical: support@proclima.com.au | General: welcome@proclima.com.au

www.proclima.com.au





Technical Data

Cover fleece + protective layer:	PP microfibre fleece		
Membrane:	Monolithic TEEE [†] film		
Reinforcement:	PP Scrim		
UV stability and outdoor exposure:	180 Days	ASTM G155	
Duty classification:	Extra Heavy	AS/NZS 4200.1-2017	
Vapour classification:	Class 4 (Permeable)	AS/NZS 4200.1-2017	
Thickness:	0.90 mm ± 0.1 mm	EN1489-2	
Flammability index:	< 5	AS 1530.2-1993	
Temperature resistance:	-40 °C to +100 °C		
Heat shrinkage @ 70°C:	MD / LD	0.0%, 0.0%	ASTM D1204
Edge tear:	MD / LD	746 / 485N	TAPPI T470
Tensile strength:	MD / LD	15.9 / 11.8 kN/m	AS 1301.448s-1991
S _d value, equiv. air layer thickness:	0.15 m ± 0.03 m		ISO 12572 C (equiv. 0.765MNs/g)
Vapour permeance:	1.3072 µg/N.s		
Water control:	> 2,500 mm		EN 20811
	Pass (> 100 mm)		AS/NZS 4201.4-1994
	Water barrier		AS/NZS 4200.1-2017
Emittance:	Front / Back	0.9 / 0.9	AS/NZS 4200.1-2017
	Classification	NN	AS/NZS 4200.1-2017
Surface water absorbency:	> 200 g/m ²		AS/NZS 4201.6-1994
	High (> 100 g/m ²)		AS/NZS 4200.1-2017
Air control:	≥ 0.1 MNs/m ³		ISO 5636.5, BS 6538.3
	Air barrier		AS/NZS 4200.1-2017
Moisture shrinkage:	< 0.5 %		AS/NZS 4201.3
Surface weight:	200 g/m ² ± 10 g/m ²		EN1489-2
Electrical conductivity:	Electrically non-conductive		AS/NZS 4200.1 - 2017

THIS PRODUCT MEETS THE REQUIREMENTS OF AS/NZS 4200.1 & IS SUITABLE FOR USE IN AUSTRALIA

[†]TEEE: Thermoplastic Elastomer Ethyl Ester

IMPORTANT INFORMATION

- This product is a Class 4 vapour permeable pliable building membrane in accordance with AS 4200.1.
- This product is designed to be Extra Heavy Duty for use in the most challenging wind areas.
- This product can withstand temperatures up to 100°C and down to -40°C behind external claddings.

PRODUCT DESCRIPTION

SOLITEX MENTO® ULTRA is a UV stabilised and tear resistant synthetic weather resistive barrier (WRB). A non-porous water resistant TEEE[†] film is laminated at high temperature between two layers of spun bonded polypropylene (PP).

WEATHER EXPOSURE

This product is a weather resistive barrier (WRB) and designed to withstand up to 180 days direct exposure to UV and still fulfil the intended use for wind and water control. Exterior cladding should be detailed to prevent direct sunlight onto the membrane in service.

APPLICATION NOTES

This product is suitable for use in BAL regions 12.5 to 40 in accordance with AS 3959. Wherever non-combustible material is required by the NCC it should be noted that this product is less than 1mm thick and has a flammability index of less than 5.

Delivery Form

ID CODE	LENGTH	WIDTH	AREA	KG/ROLL	QTY
1AR02506	50 m	1.50 m	75 m ²	16.5	1



Your local support

1800 PRO CLIMA (776 254)

Technical: support@proclima.com.au | General: welcome@proclima.com.au

www.proclima.com.au

